PERMA FLEX

100% POURABLE EPOXY JOINT AND CRACK FILLER, SEALER AND WATERPROOFER

DO NOT TRANSFER TO UNMARKED CONTAINERS. KEEP OUT OF REACH OF CHILDREN CAUTIONARY INFORMATION: DO NOT USE THIS PRODUCT BEFORE READING THE MATERIAL SAFETY DATA SHEET. FOR INDUSTRIAL/PROFESSIONAL USE OYLY.

CAUTION: FOLLOW ALL CAUTIONARY INFORMATION CONTAINED ON PERMA FLEX MIX A AND PERMA FLEX MIX B LABELS AND MSDS SHEETS

CAUTION: MIX ONLY WHEN READY TO USE AS PERMA FLEX CANNOT BE STORED ONCE THE COMPONENTS HAVE BEEN MIXED. POT LIFE IS ABOUT 45 MINUTES TO 1 HOUR DEPENDING ON TEMPERATURE

WARNING: MAY CAUSE SENSITIZATION OR OTHER ALLERGIC RESPONSES. AVOID INHALATION OF VAPOR. USE GOOD VENTILATION, PARTICULARLY IF MATERIAL IS HEATED OR SPRAYED. PREVENT ALL CONTACT WITH SKIN OR EYES. WEAR PROTECTIVE CLOTHING, GOGGLES, GLOVES AND/OR BARRIER CREAMS. IF CONTACT WITH SKIN OCCURS, WASH IMMEDIATELY WITH SOAP AND WATER. IN CASE OF CONTACT WITH EYES, FLUSH IMMEDIATELY WITH WATER AND CONTACT PHYSICIAN.

PERMA FLEX IS UNIQUE IN ITS ABILITY TO BOND TO DAMP SURFACES. THUS PERMA FLEX MAY BE USED INDOORS AND OUTDOORS, OR ON SLABS WHERE IT IS DIFFICULT, PROVIDES A HIGH STRENGTH LIQUID CRACK FILLER AND SEALER. PERMA FLEX IS A UNIQUE AND COMPLETE LIQUID EPOXY SYSTEM. USAGE IS SIMPLE EVEN UNDER THE MOST EXTREME CONDITIONS. WHEN MIXED, PERMA FLEX

DIRECTIONS: CLEAN SURFACES OF LOOSE AGGREGATE, DIRT, GREASE AND OIL. THE USE OF SIMPLE NOB MANUFACTURED BY ELS. IS RECOMMENDED. SURFACES MUST BE CLEAN AND SOUND FOR PROPER ADHESION. PREMIX CONTAINER A WITH CONTAINER B (2 TO 1 BY VOLUME). IF NOT IMPOSSIBLE, TO GET THE SURFACE ABSOLUTELY DRY.

SHOULD BE PUSHED FLAT WITH A PUTTY KNIFE. CRACK FILLING: REMOVE ALL LOOSE MATERIAL FROM AREA. MIX AS DIRECTED AND POUR INTO CRACK. MATERIAL SHOULD SELF LEVEL - ANY EXCESS, MATERIAL

2) WATERPROOFING: APPLY PREMIXED PERMA FLEX TO SURFACE WITH A PAINT BRUSH OR ROLLER AT A RATE OF 175 TO 200 SQ. FT. PER GALLON.

PERMA FLEX REMAINS WORKABLE FOR APPROXIMATELY 30 TO 45 MINUTES

PERMA FLEX WILL WITHSTAND LIGHT TRAFFIC IN 8 HOURS; HEAVIER IN 24 HOURS

NOTE: BOTH POT LIFE AND CURE TIME IS SHORTENED AS TEMPERATURE RISES AND IS LENGTHENED AS TEMPERATURE IS LOWERED. PERMAFLEX SHOULD NOT BE USED

WHEN TEMPERATURE IS BELOW 40 DEGREES F.

CLEAN UP: CLEAN TOOLS AND EQUIPMENT IMMEDIATELY AFTER USE WITH TOPSOLV MANUFACTURED BY E.L.S. PRODUCTS CORP

